

INVESTIGATIONAL STUDY ON THE INFLUENCE OF SUGARCANE BAGASSE ASH AND NYLON FIBRE IN THE STABILIZATION OF EXPENSIVE SOIL

Ashu Parihar¹, Anoop Sharma²,

¹PG student, Dept. of Civil Engineering, Sri Sai College of Engineering and Technology Badhani, Pathankot, Punjab

² Assistant Professor, Dept. of civil Engineering, Sri Sai College of Engineering and Technology, Badhani, Pathankot Punjab

Abstract - An Abstract - Soil stabilization is done to improve its engineering performance such as shear strength, compressibility and permeability. Soil stabilization may be physical, chemical, biological or combined methods to meet an engineering purpose. Soft clay is a problematic soil from civil engineering construction point of view. To make them more feasible to construction purposes, numerous materials have been used. In this paper stabilization of clayey soil using Nylon Fibre and Sugarcane Bagasse Ash was evaluated. Experiments were conducted on soil treated with Rice Husk Ash only and soil treated with both Sugarcane Bagasse Ash and Nylon Fibre. The methodology used was first to find out the optimum Sugarcane Bagasse Ash that can be utilized in untreated soil. Further various percentage of Nylon Fibre (1.0, 1.5 and 2.0) was added at various Sugarcane Bagasse Ash percentages (15, 20, and 25) and the optimum was found out. The optimum percentage was obtained from standard proctor test, and the strength was obtained from unconfined compressive strength test and California bearing ratio test. The optimum percentage of Nylon Fibre and Sugarcane Bagasse Ash was obtained as 1.5 and 20% by weight of soil, respectively. Result of optimum percentage on unconfined compressive strength, California bearing ratio test and plasticity characteristics of treated soil were determined over a curing period of 1 day and 7 days. The strength of soil stabilized with Nylon Fiber and Sugarcane Bagasse Ash was found to be improved, and the strength of treated soil was more in the case of combination of Sugarcane Bagasse Ash and Nylon Fibre.

Key Words: Sugarcane Bagasse Ash¹, Nylon Fibre², CBR test³, UCS test⁴.

1. INTRODUCTION

Expansive soils are the soils which have high shrinkage and swelling characteristics and lower strength when it came in contact with water. These soils are very sensitive to variations in water content and show excessive volume changes and has high compressibility. This highly plastic soil may create cracks and damage the construction work done above these type of soils.

In India, expansive soil covers nearly about 20% of the land and includes approximately the entire Deccan Plateau. They

are mostly black and reddish brown in colour and are generally found with layer thickness between 0.5 m to 10 m below the surface. Because the expansive soil is prone to volume changes when it came in contact with the water by rain or water table capillary action, it will get expand and may cause lifting of the structures built over it. So, these soils are not suitable for construction works until they are properly stabilized which can increase the low bearing capacity of expansive soils.

In India, nearly 46% of total land is covered by Alluvial soil which is the most important soil type of our country. Other soils such as Black cotton soil, desert soil, laterite soil and marine soil are also the important soil groups of India. The Alluvial soil and the black cotton soil mainly consists of clay which is very fine soil and it's the main constituent of expansive soils and due to the cohesive nature of clay, these soils absorb large amounts of water and show swelling characteristics which create problems such as bulging of soil, low bearing strength of soil, and can cause cracks in the foundations.

2. Literature Review

Al-Jaberi et al. (2017) In their study, they improved the properties of poor subgrade soil using Cement Kiln Dust. They investigate the effects of CKD on the properties of the poor subgrade soils using CBR testing method with different doses of CKD (5%, 10%, 15%, 20%, 25%, and 30% by the dry weight of the selected soil) in combination with different curing periods (1 day, 3 days, 7 days, 14 days, and 28 days). They concluded that the optimum amount of CKD to be used is 20% and the optimum curing period for this came to be 14 days.

Keerthi et al. (2017) The stabilization of clayey soil is done using CKD. In which the CKD proportions is varied from 0 to 50% by weight of soil. In their study, it is found that the Unconfined Compressive Strength of soil is increased when CKD is added 50% as compared to 0% CKD. They also concluded that the optimum quantity of CKD for light applications is varied between 12-30% however for heavy applications, CKD content of upto 50% can be used.

Rokade et al. (2017) Addition of nylon fibre along with fly ash to measure the change in the strength parameters of black cotton soil. The CBR of the soil was determined by conducting three series of tests. Tests were carried out on the BC soil mixed with varying percentage of fly ash, from 10% to 40% out of which 20% came out to be optimum. Then, nylon fibre with aspect ratios (length/ diameter) 20, 40, 60 and 80 and fiber contents were varied from 0.25% to 1.5% with 0.25% interval, out of which 0.75% of fibre content is considered as optimum on the basis of MDD and maximum CBR value.

Mahesh et al. (2016) Soil stabilization is used to reduce the permeability and compressibility of the soil mass in earth structures and to increase its shear strength. Soil stabilization is required to increase the bearing capacity of foundation soils. However, the main use of stabilization is to improve the natural soils for the construction of highways and airfields. CBR value is high at 10% lime + 1.5% fiber when compared to the remaining proportions. CBR value for (soil +10% lime) and (soil + 40% lime) is same. CBR gradually increases with increase in fibers upto 2% (soil + 5% lime).

Wang et al. (2016) The Unconfined Compression Strength of expansive soil is very less without the addition of certain additives which can increase their strength. CKD was chosen to add in various proportions. 2,4,6,8,10,12,14,16,18,20% of CKD was the proposed quantity. The UCS value rises till 10% CKD content after that when CKD quantity is further increased, the value of UCS started to decline gradually. Which concluded that 10% is the optimum value of CKD at the curing period of 28 days.

Tiwari et al. (2016) They studied the stabilization of black cotton soil using fly ash and nylon fibre. In their study, they used different combinations of fly ash as 10%,20%, 30% & 40%. 20% was their optimum value. After which they calculated the optimum value of nylon fibre from various values as 0.25%, 0.50%, 0.75%, 1%, 1.5%. From which 0.75% nylon fibre comes to be the optimum. The CBR value of soil+20% fly ash+0.75% fibre was maximum of all other readings. And the MDD was also maximum of this mix proportion.

Phanikumara et al. (2013) This paper presents the swell-consolidation characteristics of remoulded expansive clay specimens reinforced with randomly distributed nylon fibre. In the case of nylon fibre, the length of the fibre (l) was varied at 15 mm and 20 mm. As the diameter of the fibres was 1mm, the aspect ratio of the fibres used was equal to 15 and 20, respectively. The fibre content (fc) used in the testing programme was varied at 0%, 0.05%, 0.1%, 0.15%, 0.2%, 0.25% and 0.3% by the dry weight of the soil. Their result shows that the swell potential (S%) and the vertical swelling pressure also decreased with an increasing fibre content (fc) for a given fibre length. & these secondary compression decreased with an increasing length of fibre.

The value of the secondary consolidation coefficient (C_α) for fibre-reinforced specimens was less than that for the unreinforced specimen.

Ismaiel et al. (2013) This work dealt with a chemical stabilization of an expansive high plastic soil of using cement kiln dust (CKD) and cement kiln dust with lime (CaO) to reduce their swelling and improve their geotechnical properties. Various tests were conducted such as plasticity tests, compaction test, Unconfined Compressive strength test. According to the test results, optimum content of the cement kiln dust was 16% (CKD) & The optimum content of the cement kiln dust with the lime was 14% (CKD) with 3% (Cao).

Praveen et al. (2011) Studied the effect of Polypropylene fibre on CKD stabilized soil. The soil they used is Black cotton soil and the various proportions of CKD were 3%, 5%, & 8%. The proportions of PP fibre were taken as 0.25%, 0.50% & 1%. UCS test and CBR test were conducted and the value of both UCS test and CBR test was maximum at CKD content of 8% and fibre content of 1%. So this proportion was considered to be the optimum.

Kameshwar Rao Tallapragada et al. (2009) Their work is undertaken to research the benefits of fiber reinforced subgrade. They used two fibres: nylon fibre and monofilament. The main tests performed were CBR test & UCS test to check the strength. Three proportions were prepared as 0.75%, 1.5% & 2.25%. Their result shows CBR value of Black Cotton soil also increases considerably due to addition of the fibers in soil. From UCS test it was found that Maximum Stress value of soil increases with increasing aspect ratio of nylon fibre.

2. Materials and Method

Section 2.1- Sugar Cane Bagasse Ash and Nylon Fiber as stabilizer

2.1.1 Sugar Cane Bagasse Ash

Sugar cane bagasse ash (SCBA) is an abundant byproduct of the sugar and ethanol industry. SCBA is generally used as a fertilizer or is disposed of in landfills, which has led to intensified environmental concerns. In recent years, SCBA research has mainly been focused on utilization in construction materials due to the abundance and pozzolanic characteristics of SCBA. In this paper, a comprehensive review of the state-of-the-art morphology, physical properties, chemical composition, and mineralogical composition of SCBA is presented. Studies indicate that SCBA is a potentially promising construction material. The applications of SCBA as a pozzolanic material, a new source for preparing alkali-activated binders, aggregates, and fillers in construction materials, are summarized.



2.1.2 Nylon Fibre

Nylon is a polymer developed to reproduce the properties of nylon 66. It is a semi crystalline polyamide. Nylon 6 fibres are tough, possessing high tensile strength, as well as elasticity and lustre and has excellent abrasion resistance. Nylon 6 is generally white but can be dyed to in a solution bath prior to production for different color results. Nylon fibre is used in soil stabilization to increase the load carrying capacity of soil by the frictional interaction between the soil and the reinforcement and it should be randomly mixed with soil in proper proportions. Nylon fibre has good elasticity behaviours and it is highly resistant to abrasion and temperature so it can be used in high temperatures also. The aspect ratio of nylon fibre ie. L/D ratio of fibre is the deciding factor for the size that is to be used.



Section 2.2 Methods

The present project can serve as an effective method to utilize industrial wastes Sugarcane Bagasse Ash and Nylon Fibre in the construction of low cost rural roads and stabilize the subgrade of pavements where the soil is expansive in nature. These various tests needs to be carried out on samples selected for study:

- [1] Liquid Limit test and plastic limit test needed to be performed with the help of Cassegrande's Apparatus first on virgin soil and then the various proportions of the mix. The Plasticity Index of the Optimum Mix should be always less than that of virgin soil.
- [2] Standard Proctor Test is carried out to calculate Optimum Moisture Content (OMC) and Maximum Dry Density (MDD) of virgin soil which is then compared to MDD of mix proportions. The MDD of

the optimum mix should always be higher than pure soil.

- [3] California bearing ratio test is conducted to calculate CBR Values at different proportions with material
- [4] Unconfined compression strength test is conducted to calculate UCS Values at different proportions with material

Table-1: Properties of soil used

S.No.	Properties	Result
1.	Liquid limit (%)	48
2.	Plastic limit (%)	26
3.	Plasticity Index (%)	22
4.	Specific Gravity	2.69
5.	Maximum Dry Density (KN/m ³)	18.25
6.	Optimum Moisture Content (%)	13.6
7.	Soil Classification	CI (Intermediate Compressive Clay)

Table-2: Properties of Sugarcane Bagasse Ash

S.No	Compound	Value (%)
1	Sio2	69.66
2	Al2o3	5.20
3	Fe2o3	5.19
4	Cao	4.87
5	Mgo	2.19
6	So3	0.30
7	K2o	13.93
8	Na2o	0.56
9	P2O5	3.36

Table-3: Properties of Nylon Fibre.

S.No.	Property	Value
1.	Density	1.14gm/cc
2.	Melting point	215°C
3.	Length(L)	20mm
4.	Specific gravity	0.90
5.	Diameter(D)	0.50mm
6.	Aspect ratio(L/D)	40

Results and Discussion

The soil used in this project was collected from local soil deposits in Jammu. Then the soil is prepared by doing sieving with 4.75mm sieve, the quantity retaining on 4.75mm sieve is taken out of the sample soil and the soil passing 4.75mm sieve is oven dried with a temperature of 105°C for 24 hours. All the lumps if present in the soil were cleared with hammer.

Tests conducted in the laboratory for different objectives are as follows:

- [1] Liquid Limit Test (Casagrande's method)
- [2] Plastic Limit test (Thread method)
- [3] Standard Proctor test (OMC and MDD)
- [4] California Bearing Ratio test
- [5] Unconfined Compression strength test

MIX PROPORTIONS USED

Different proportions of different materials were used in the project work. Sugar Cane Bagasse Ash was 10%, 20%, & 30% and Nylon fibre used was 1%, 1.5% & 2.0%. Now, S=Soil, SCBA= Sugar Cane Bagasse Ash, N=Nylon fibre

EXPERIMENTAL RESULTS

Section-1- Standard Proctor Test

Table no:4- Results of OMC and MDD for mix proportions of Soil, SCBA and Nylon Fibre

SOIL:SCBA:NYLON FIBRE	MDD(kN/m ³)	OMC (%)
79.5:20:0.5	17.80	14.45
79:20:1	17.10	15.20
78.5:20:1.5	16.90	15.65




Chart-1: variations b/w MDD and OMC of SCBA, Nylon Fibre & soil with different proportions

Section-2: Unconfined Compression Strength Test

Table-5: Results of UCS of Sugercane Bagasse Ash and Nylon Fibre Mix with Soil

Clayey Soil :SCBA: N.F	Curing Period (Days)	UCS (kN/m ²)
100 : 00	7	232.05
79.5:20:0.5	7	290.15
79:20:1.0	7	337.43
78.5:20:1.5	7	363.61




Chart-2: Variations b/w UCS Values of Clayey soil, Sugercane Bagasse Ash and Nylon Fibre with different proportions

Section-3: California Bearing Ratio Test

Table-6: Results of CBR of Sugercane Bagasse Ash and Nylon Fibre Mix with Soil.

CS: SCBA: N.F	CBR (%)
100:00:00	3.87
79.5:20:0.5	5.17
79:20:1.0	5.52
78.5:20:1.5	6.16




Chart-3: Variations b/w CBR Values of Clayey soil, Sugercane Bagasse Ash and Nylon Fibre with different proportions

DISCUSSIONS

MODIFIED PROCTOR TEST:

•An increase of OMC from 13.6 to 15.10% and decrease of M.D.D. from 18.25 to 17.10% when the percentages of Sugercane Bagasse ash are used as 15%, 20% and 25% respectively.

•There is an also increase of OMC from 13.6 to 15.20% and decrease of MDD from 15.14 to 14.55% when the percentages of Nylon Fibre are used as 1.0%, 1.5% and 2.0% respectively.

•There is an also increase of OMC from 14.45 to 15.65% and decrease of MDD from 17.80 to 16.90% when the percentages of Nylon Fibre vary from 0.50%, 1.0% and 1.5% and Sugercane Bagasse ash is fixed at 20%.

• Specific gravity of Sugercane Bagasse ash is lower than as compared to soil. So MDD is decreased and OMC is increased.

•There is an expansion in OMC when the amount of Rice husk ash is expanded. The purpose for of this pozzolanic response of Rice husk powder with soil that needs more water for completion of cation trade response.

•With Sugercane Bagasse ash kept constant at 20% MDD decreases with an addition of Nylon Fibre content in soil and Sugercane Bagasse ash mix. The reason behind of such behavior is Sugercane Bagasse ash is lighter in weight and it has high water absorption properties because of presence of calcium oxide and hence OMC increases with increase of Sugercane Bagasse ash content.

CBR TEST:

•Presence of pozzolanic compounds in Sugercane Bagasse ash and CaOH available in soil might be increase the CBR value due to formation of cementitious compounds in soil. Due to excess of Sugercane Bagasse ash in soil ultimately occupies spaces within sample because of this Sugercane Bagasse ash could not be mobilized for the reaction at 20% of Sugercane Bagasse ash in soil.

•The CBR value of virgin soil is 3.87 and it increases to 1.31 times with addition of 20% Sugercane Bagasse ash when observed in soaked conditions. This enhancement is because of binding action of Sugercane Bagasse ash.

•The CBR value of virgin soil is 3.87 and it increase to 1.59 times when Sugercane Bagasse ash 20% and Nylon Fibre 1.5% is added to virgin soil. This enhancement in CBR may be because of the gradual formation of hydration compounds in the soil due to the reaction between the stabilizers and the essentials particle present in the soil.

UCS TEST:

•UCS value of virgin soil enhances fundamentally with expansion of Sugercane Bagasse ash contents. The UCS value increment from 232.05kN/m² to 312.73kN/m² with expansion of Sugercane Bagasse ash upto 20% in the wake of curing time of 7 days. U.C.S. value decreases with more expansion of Sugercane Bagasse ash. The expansion in U.C.S. value might be a direct result of the slow advancement of the cementitious mixes in the soil by the response between pozzolanic mixes in Sugercane Bagasse ash and CaOH accessible in soil.

•The UCS values of virgin soil also improves considerably with expansion of Sugercane Bagasse ash 25% and Nylon Fibre 1.5%. The value increases from 232.05kN/m² to 363.61kN/m² with addition of Sugercane Bagasse ash and Nylon Fibre.

•The reason behind of this when Sugercane Bagasse ash and Nylon Fibre comes in contact with water, pozzolanic reactions takes place during the curing period.

CONCLUSIONS

Following conclusions can be inferred on the basis of the experiments performed:

- [1] Sugarcane Bagasse ash is a waste product of cement manufacturing process which can be effectively used in the stabilization process of soil due to its cementitious properties that helps in increasing the strength of soil.
- [2] Nylon fiber on the other hand is a cheaply available material which can be added to soil in less quantities to make big changes in its strength parameters.
- [3] The optimum value of Sugarcane Bagasse ash is used for this work was 20% because of the optimum value of C.B.R. is found at 20% of Sugarcane Bagasse ash when added to soil.
- [4] 4.The C.B.R value increases with increase of Nylon Fibre along with fixed quantity of Rice Husk Ash. It increased 1.59 times from the untreated soil.
- [5] The optimum value of Nylon Fibre and Sugarcane Bagasse ash required for soil stabilization is 1.5 % and 20% by weight of soil respectively.
- [6] Unconfined compressive strength increases with increase of quantity of Nylon Fibre and with fixed quantity of Sugarcane Bagasse ash. The value of Unconfined compressive strength is increased 1.34 times from the untreated soil.

References

- [1] Ahmed Mancy Mosa, Amer Hasan Taher, Layth A. Al-Jaberi(2017) "improvement of poor subgrade soil using cement kiln dust".
- [2] B.R. Phanikumar, Ravideep Singla (2016) "Swell-consolidation characteristics of fibre reinforced expansive soils".
- [3] Dr. Siddhartha Rokade, Rakesh Kumar, Dr. P.K. Jain(2017) "Effect of Inclusion of Fly-Ash and Nylon Fiber on Strength Characteristics of Black Cotton Soil". EJGE Vol. 22 [2017].
- [4] Hesham A. H. Ismaiel (2013) "Cement Kiln Dust Chemical Stabilization of Expansive Soil Exposed at El-Kawther Quarter, Sohag Region, Egypt".
- [5] M.Heeralal, G.V. Praveen(2011) " A study on effect of fiber on cement kiln dust stabilized soil". JERS/Vol. II/ Issue IV/October-December, 2011/173-177
- [6] M.K. Rahman, S. Rehman & O.S.B. Al-Amoudi(2011) "Literature review on cement kiln dust usage in soil and waste stabilization and experimental investigation".
- [7] Kameshwar Rao Tallapragada, Anuj Kumar Sharma, Tarulata Meshram(2009) "laboratory investigation of use of synthetic fibers to minimize swell in expansive subgrades". IGC 2009, Guntur, INDIA
- [8] Pallavi, Pradeep Tiwari, Dr P D Poorey(2016) "Stabilization of Black Cotton Soil using Fly Ash and Nylon Fibre". IRJET Volume: 03 Issue: 11 | Nov - 2016
- [9] Indian Standard Code IS 2720-16, IS 2720-10.